

Patent Abstracts of Japan

PUBLICATION NUMBER : 11302020  
PUBLICATION DATE : 02-11-99


APPLICATION DATE : 20-04-98  
APPLICATION NUMBER : 10144958

APPLICANT : UBE IND LTD;

INVENTOR : TANAKA YOSHIKUMI;

INT.CL. : C01G 45/12 H01M 4/02 H01M 4/58  
H01M 10/40

TITLE : LITHIUM MANGANESE COMPOUND  
OXIDE, ITS PRODUCTION AND ITS  
USE



LiMn2O4.25-Li4.1Mn4.9O11.85-LiMn2O6 系三角ダイアグラム  
による非化学量組成のスピンル化合物の表示  
(斜線部は特許請求範囲を表す)

ABSTRACT : PROBLEM TO BE SOLVED: To produce a lithium manganese compound oxide for the positive electrode of a lithium cell.

SOLUTION: The lithium manganese compound oxide is a compd. consisting of Li, Mn and O, represented by the formula  $\text{Li}_{1+x}\text{Mn}_{2-y}\text{O}_4$  (where  $-0.01 < x < 0.15$  and  $0 < y < 0.15$ ) and having a cubic spinel structure. The atomic ratio of Li to Mn is 0.52-0.59 and the average oxidation number of Mn is 3.45-3.65. The multiple oxide has 0.821-0.824 nm lattice constant, 60-180 nm crystallite diameter and 1.0-3.7  $\text{m}^2/\text{g}$  BET specific surface area, contains at least  $\geq 3\%$  primary particles having  $\geq 1 \mu\text{m}$  particle diameter and has 1.0-15.0  $\mu\text{m}$  median diameter on the particle size distribution curve measured by a laser diffraction scattering method, an aggregation index of 5-20 and  $\geq 55\%$  press molding density.

COPYRIGHT: (C) JPO

**THIS PAGE BLANK (USPTO)**